

## Polyfort PPC HI K1888

Polypropylene Copolymer

LyondellBasell Industries

Engineering Plastics

### Product Description

High impact PP copolymer, suitable for injection molding and extrusion

### General

|                   |             |                          |
|-------------------|-------------|--------------------------|
| Features          | • Copolymer | • High Impact Resistance |
| Processing Method | • Extrusion | • Injection Molding      |

| Physical                                   | Nominal Value (English)    | Nominal Value (SI)         | Test Method          |
|--------------------------------------------|----------------------------|----------------------------|----------------------|
| Density                                    | 0.900 g/cm <sup>3</sup>    | 0.900 g/cm <sup>3</sup>    | ISO 1183/A           |
| Melt Volume-Flow Rate (MVR) (250°C/5.0 Kg) | 3.0 cm <sup>3</sup> /10min | 3.0 cm <sup>3</sup> /10min | ISO 1133             |
| Mechanical                                 | Nominal Value (English)    | Nominal Value (SI)         | Test Method          |
| Tensile Modulus                            | 145000 psi                 | 1000 MPa                   | ISO 527-1/1A/1       |
| Tensile Stress (Yield)                     | 2900 psi                   | 20.0 MPa                   | ISO 527-2/1A/50      |
| Tensile Strain (Yield)                     | 12 %                       | 12 %                       | ISO 527-2/1A/50      |
| Impact                                     | Nominal Value (English)    | Nominal Value (SI)         | Test Method          |
| Charpy Notched Impact Strength             |                            |                            | ISO 179/1eA          |
| -22°F (-30°C)                              | 1.9 ft·lb/in <sup>2</sup>  | 4.0 kJ/m <sup>2</sup>      |                      |
| 73°F (23°C)                                | 31 ft·lb/in <sup>2</sup>   | 66 kJ/m <sup>2</sup>       |                      |
| Charpy Unnotched Impact Strength           |                            |                            | ISO 179/1eU          |
| -22°F (-30°C)                              | No Break                   | No Break                   |                      |
| 73°F (23°C)                                | No Break                   | No Break                   |                      |
| Thermal                                    | Nominal Value (English)    | Nominal Value (SI)         | Test Method          |
| Vicat Softening Temperature                | 136 °F                     | 58.0 °C                    | ISO 306/B50          |
| Electrical                                 | Nominal Value (English)    | Nominal Value (SI)         | Test Method          |
| Surface Resistivity                        | > 1.0E+15 ohms             | > 1.0E+15 ohms             | IEC 60093            |
| Volume Resistivity                         | > 1.0E+13 ohms·m           | > 1.0E+13 ohms·m           | IEC 62631-3-1        |
| Flammability                               | Nominal Value (English)    | Nominal Value (SI)         | Test Method          |
| Burning Rate                               |                            |                            |                      |
| 0.0787 In (2.00 Mm)                        | < 3.9 in/min               | < 100 mm/min               | ISO 3795             |
| 0.0787 In (2.00 Mm)                        | < 3.9 in/min               | < 100 mm/min               | FMVSS 302            |
| Flammability Classification                |                            |                            | IEC 60695-11-10, -20 |
| 0.06 In (1.6 Mm)                           | HB                         | HB                         |                      |

### Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications



Polyfort PPC HI K1888

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics



| Injection              | Nominal Value (English) | Nominal Value (SI) |
|------------------------|-------------------------|--------------------|
| Drying Temperature     | 176 °F                  | 80 °C              |
| Drying Time            | 2.0 to 3.0 hr           | 2.0 to 3.0 hr      |
| Processing (Melt) Temp | 428 to 500 °F           | 220 to 260 °C      |
| Mold Temperature       | 86 to 140 °F            | 30 to 60 °C        |
| Injection Rate         | Moderate-Fast           | Moderate-Fast      |

Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.

Ensure good mold venting

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.

