

Technical Data Sheet

Pro-fax 6301



Polypropylene, Homopolymer

Product Description

Pro-fax 6301 polypropylene homopolymer is available in spherical particle form. This resin is typically used for mixing with pigments and other additives to make polymer concentrates or masterbatches.

Pro-fax 6301 has very minimal stabilization, which allows wide design latitude for compounders. Additional stabilization is required to protect the resin during melt processing and throughout its useful life.

Please note that any additives compounded into this resin will require a re-assessment of its FDA status.

Regulatory Status

For regulatory compliance information, see *Pro-fax* 6301 [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

| | |
|--------------------------|---|
| Status | Commercial: Active |
| Availability | North America |
| Application | Colour Concentrates; Polymer Modifier; Wood Composites |
| Market | Compounding |
| Processing Method | Compounding |
| Attribute | Dispersible; Good Stiffness; High Filler Loading Capability |

| Typical Properties | Nominal Value | English Units | Nominal Value | SI Units | Test Method |
|---------------------------------------|---------------|-------------------|---------------|-------------------|-------------|
| Physical | | | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 12 | g/10 min | 12 | g/10 min | ASTM D1238 |
| Density, (23 °C) | 0.90 | g/cm ³ | 0.90 | g/cm ³ | ASTM D792 |
| Mechanical | | | | | |
| Flexural Modulus | | | | | |
| (0.05 in/min, 1% Secant, Procedure A) | 210000 | psi | | | ASTM D790 |
| (1.3 mm/min, 1% Secant, Procedure A) | | | 1450 | MPa | ASTM D790 |
| Tensile Strength at Yield | | | | | |
| (2 in/min) | 4900 | psi | | | ASTM D638 |
| (50 mm/min) | | | 34 | MPa | ASTM D638 |
| Tensile Elongation at Yield | 11 | % | 11 | % | ASTM D638 |
| Impact | | | | | |
| Notched Izod Impact Strength | | | | | |
| (73 °F, Method A) | 0.6 | ft-lb/in | | | ASTM D256 |
| (23 °C, Method A) | | | 32 | J/m | ASTM D256 |
| Thermal | | | | | |
| Deflection Temperature Under Load | | | | | |
| (66 psi, Unannealed) | 200 | °F | | | ASTM D648 |
| (0.45 MPa, Unannealed) | | | 93 | °C | ASTM D648 |

Notes

These are typical property values not to be construed as specification limits.

