

## Technical Data Sheet

### Purell HP372P



Polypropylene, Homopolymer

#### Product Description

Purell HP372P is a polypropylene homopolymer with a gamma - ray stabilizing additivition for use in injection molding applications.

Purell HP372P exhibits a high fluidity and very good transparency.

Purell HP372P is primarily designed for empty disposable three - part syringes which are not to be supplied in the same package as the medication itself and for other medical applications.

All potential activities for applications in the pharmaceutical, medical device, laboratory and diagnostics area have to be discussed with the relevant Technical and Business contacts first. To discuss a medical/pharmaceutical application please contact your local Lyondellbasell reference or your local Distributor.

<b>Application</b>	Healthcare Applications; Syringes
<b>Market</b>	Healthcare
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Autoclavable; E-Beam Sterilizable; Ethylene Oxide Sterilisation; Medium Flow; Medium Transparency; Radiation Sterilizable

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Tensile Modulus	1250	MPa	ISO 527-1, -2
Tensile Stress at Yield	31	MPa	ISO 527-1, -2
Tensile Strain at Break	>50	%	ISO 527-1, -2
Tensile Strain at Yield	15	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	6	kJ/m <sup>2</sup>	ISO 179
<b>Hardness</b>			
Ball Indentation Hardness, (H 358/30)	60	MPa	ISO 2039-1
<b>Thermal</b>			
Vicat Softening Temperature, (A50)	150	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	80	°C	ISO 75B-1, -2
<b>Optical</b>			
Haze, (1 mm - injection molded disc)	15	%	ASTM D1003

#### Notes

These are typical property values not to be construed as specification limits.

