

## Technical Data Sheet

### Sequel 1825 C2 UV 848 BLK

Polypropylene Compounds



#### Product Description

Sequel 1825 C2 UV 848 BLACK thermoplastic polyolefin is designed for automotive and heavy-truck applications that require energy management combined with ductility, stiffness and impact resistance over a broad temperature range. This material exhibits excellent processability and dimensional stability

Application	Automotive Parts; Bumpers; Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Ductile; Good Dimensional Stability; Good Processability; Good Stiffness; Low Temperature Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	15	g/10 min	ISO 1133-1
Density, (23 °C)	1.16	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus	2400	MPa	ISO 178
Tensile Stress at Yield, (23 °C, 50 mm/min)	19	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	30	kJ/m <sup>2</sup>	ISO 180/1A

#### Notes

These are typical property values not to be construed as specification limits.

