

## Sequel 1733HI

### Compounded Polyolefin

#### Product Description

Sequel 1733HI thermoplastic polyolefin is designed for large, painted, automotive exterior applications that require dimensional stability over a broad temperature range. This material exhibits excellent processability.

#### Product Characteristics

<b>Status</b>	Commercial: Restricted
<b>Test Method used</b>	ISO
<b>Processing Methods</b>	Injection Molding
<b>Features</b>	Good Dimensional Stability, High Impact Resistance , Paintable, Good Processability
<b>Typical Customer Applications</b>	Exterior Applications

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density	ISO 1183	1.07	g/cm <sup>3</sup>
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	14	g/10 min
<b>Mechanical</b>			
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	21.0	MPa
Note: 150x10x4 mm specimen			
Flexural modulus (2 mm/min)	ISO 178	1780	MPa
Note: 80x10x4mm specimen			
<b>Impact</b>			
Multiaxial Impact Strength (23 °C, 2.2 m/s)	ASTM D3763	19	J
<b>Additional Information</b>			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrinkage recommendations.			

#### Notes

Typical properties; not to be construed as specifications

