

Technical Data Sheet

Softell TKG 317NU NATL

Polypropylene Compounds



Product Description

Softell TKG 317NU NATL is a 25% glass fiber reinforced PP copolymer with superior dimensional stability, high stiffness, good surface appearance, and excellent scratch resistance. Product is available as natural pellet form.

Application	Automotive Parts; Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Dimensional Stability; Good Surface Finish; Low Gloss; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	8	g/10 min	ISO 1133-1
Density, (23 °C)	1.06	kg/m ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	4500	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	69	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	11	kJ/m ²	ISO 179
(-30 °C)	7.3	kJ/m ²	ISO 179
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	158	°C	ISO 75B-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			

Notes

These are typical property values not to be construed as specification limits.

