

Technical Data Sheet

Hifax BC 72G T/1 2078 (YZ9A)

Polypropylene Compounds



Product Description

Hifax BC 72G T/1 2078 is a talc filled PP copolymer, with good flowability, high stiffness, medium impact resistance and good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 2078 color version.

Application	Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Stiffness; Good UV Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C)	1.00	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus	1900	MPa	ISO 178
Tensile Stress at Yield	22	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	8	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	108	°C	ISO 75B-1, -2

