

Technical Data Sheet

Hostacom X 4323/3 S63 100051

Polypropylene Compounds



Product Description

Hostacom X 4323/3 S63 100051 is a 20% talc filled PP copolymer, with excellent impact/stiffness balance and good flowability, good scratch and blooming resistance at elevated temperatures. Product is available as a customized color matched, pellet form. Please contact lyondellbasell for shrinkage recommendations. This grade is delivered in 100051 color version.

Application Automotive Parts; Interior Trims

Market Automotive

Processing Method Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7	g/10 min	ISO 1133-1
Density, (23 °C)	1.06	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2200	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched, (23 °C)	8.5	kJ/m ²	ISO 179-1/1eA

Notes

These are typical property values not to be construed as specification limits.

