

Qr Resin QR-4165

Polyphenylene Ether + PS

LyondellBasell Industries

Engineering Plastics

Product Description

Flame Package available as: 94V-0 (0.24")/ 94V-1 (0.0625")

General


Features	• Flame Retardant	• Good Toughness
Appearance	• Black	• Grey
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.08	1.08 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (280°C/2.16 Kg)	10 g/10 min	10 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	9000 psi	62.1 MPa	ASTM D638
Flexural Modulus	360000 psi	2480 MPa	ASTM D790
Flexural Strength (Yield)	14000 psi	96.5 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
-20°F (-29°C)	1.8 ft·lb/in	96 J/m	
73°F (23°C)	3.0 ft·lb/in	160 J/m	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	285 °F	141 °C	
264 Psi (1.8 Mpa), Unannealed	250 °F	121 °C	



Qr Resin QR-4165

Polyphenylene Ether + PS
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	220 to 235 °F	104 to 113 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Drying Time, Maximum	6.0 hr	6.0 hr
Suggested Max Moisture	0.02 %	0.02 %
Rear Temperature	380 to 400 °F	193 to 204 °C
Middle Temperature	420 to 440 °F	216 to 227 °C
Front Temperature	460 to 480 °F	238 to 249 °C
Nozzle Temperature	460 to 480 °F	238 to 249 °C
Processing (Melt) Temp	440 to 480 °F	227 to 249 °C
Mold Temperature	150 to 200 °F	66 to 93 °C

Notes

These are typical property values not to be construed as specification limits.

