

Network Polymers San 330

Styrene Acrylonitrile
LyondellBasell Industries
Engineering Plastics

General			
Features	• High Flow		
Agency Ratings	• FDA 21 CFR 181.32(a)(3)(ii)		
Appearance	• Natural Color		
Forms	• Granules		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.07	1.07 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹			ASTM D1238
200°C/5.0 Kg	8.0 g/10 min	8.0 g/10 min	
230°C/3.8 Kg	31 g/10 min	31 g/10 min	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield)	10000 psi	68.9 MPa	ASTM D638
Flexural Modulus - Tangent ³	500000 psi	3450 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	0.40 ft·lb/in	21 J/m	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	120	120	ASTM D785


Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed, 0.125 In (3.18 Mm)	196 °F	91.1 °C	
Vicat Softening Temperature	212 °F	100 °C	ASTM D1525 ⁴

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	HB	HB	UL 94



Network Polymers San 330

Styrene Acrylonitrile
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Shot Size	40 to 75 %	40 to 75 %
Rear Temperature	320 to 360 °F	160 to 182 °C
Middle Temperature	360 to 430 °F	182 to 221 °C
Front Temperature	380 to 450 °F	193 to 232 °C
Nozzle Temperature	380 to 450 °F	193 to 232 °C
Processing (Melt) Temp	380 to 420 °F	193 to 216 °C
Mold Temperature	80 to 170 °F	27 to 77 °C
Injection Pressure	60.0 to 1100 psi	0.414 to 7.58 MPa
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	75.0 to 150 psi	0.517 to 1.03 MPa
Clamp Tonnage	2.0 to 3.0 tons/in²	2.8 to 4.1 kN/cm²

Notes

- ¹ Procedure A
- ² 2.0 in/min (51 mm/min)
- ³ 0.050 in/min (1.3 mm/min)
- ⁴ Loading 1 (10 N)

Notes

These are typical property values not to be construed as specification limits.

