

Network Polymers San 270

Styrene Acrylonitrile
LyondellBasell Industries
Engineering Plastics

General			
Appearance	• Clear/Transparent	• Natural Color	
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.07	1.07 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 Kg)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	10000 psi	68.9 MPa	ASTM D638
Flexural Modulus - Tangent ²	483000 psi	3330 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 In (3.18 Mm)	0.40 ft·lb/in	21 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	86	86	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed, 0.125 In (3.18 Mm)	192 °F	88.9 °C	ASTM D648
Vicat Softening Temperature	225 °F	107 °C	ASTM D1525
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.6 Mm))	HB	HB	UL 94
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Light Transmittance	89.0 %	89.0 %	ASTM D1003
Haze	1.10 %	1.10 %	ASTM D1003

Notes

¹ 2.0 in/min (51 mm/min)

² 0.050 in/min (1.3 mm/min)

Notes

These are typical property values not to be construed as specification limits.

