

Duragrip DGR 6070BK

Thermoplastic Elastomer

LyondellBasell Industries

Engineering Plastics

Product Description

DuraGrip® 6070BK is a general purpose Thermoplastic Elastomer (TPE) designed for injection molding and extrusion processes. It has a high coefficient of friction, low melt viscosity and bonds well to polypropylene. DuraGrip® 6070BK is not hygroscopic and under normal conditions does not require drying.

General

Features	- General Purpose - Good Adhesion	- High Friction - Low Viscosity
Agency Ratings	EU 2002/96/EC (WEEE)	
RoHS Compliance	RoHS Compliant	
Appearance	Black	
Forms	Pellets	
Processing Method	Extrusion	Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	0.987	0.985 g/cm³	ASTM D792
--	0.983 g/cm³	0.983 g/cm³	ISO 1183
Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress			ASTM D412 ISO 37
100% Strain	380 psi	2.62 MPa	
300% Strain	497 psi	3.43 MPa	
Tensile Strength (Yield)	1210 psi	8.34 MPa	ASTM D412 ISO 37
Tensile Elongation (Break)	640 %	640 %	ASTM D412 ISO 37
Tear Strength ¹	163 lbf/in	28.5 kN/m	ASTM D624
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore A, 5 Sec)	72	72	ASTM D2240 ISO 868
Fill Analysis	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Viscosity (374°F (190°C), 294 Sec ⁻¹)	130 Pa·s	130 Pa·s	ASTM D3835

Additional Information


The value listed as Density -Specific Gravity, ASTM D792, was tested in accordance with ASTM D471.

The value listed as Density, ISO 1183, was tested in accordance with ISO 2781.



Duragrip DGR 6070BK

Thermoplastic Elastomer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Rear Temperature	370 to 390 °F	188 to 199 °C
Middle Temperature	390 to 410 °F	199 to 210 °C
Front Temperature	420 to 440 °F	216 to 227 °C
Nozzle Temperature	400 to 430 °F	204 to 221 °C
Processing (Melt) Temp	390 to 430 °F	199 to 221 °C
Mold Temperature	110 to 130 °F	43 to 54 °C
Injection Pressure	150 to 600 psi	1.03 to 4.14 MPa
Screw Speed	25 to 100 rpm	25 to 100 rpm

Injection Notes

Injection Speed: 1 to 3 in³/sec
Injection Time (1st Stage/Boost): 0.5 to 4 sec
Second Stage Pressure: 150 to 300 psi
Second Stage Time: 3 to 10 sec
Cooling Time: 10 to 20 sec
Back Pressure: 20 to 75 %

