

Adsyl 5 C 37 F

Advanced Polyolefin

Product Description

 $\mathit{Adsyl}\,5$ C 37 F is an advanced polyolefin, specially designed for use as a sealing layer in co-extruded film applications.

This grade features a very low seal initiation temperature. It contains slip and anti-block additives.

For regulatory information please refer to Adsyl 5 C 37 F Product Stewardship Bulletin (PSB).

| Product Characteristics | | | | |
|---|---|---------------|-------|----------|
| Status | Commercial: Active | | | |
| Test Method used | ISO AST | М | | |
| Processing Methods | BOPP, Cast Film, Double Bubble | | | |
| Features | Low Temperature Heat Sealability | | | |
| Typical Customer Applications | Double Bubble Shrink Film, Food Packaging Film, Lamination Film, Stationery Film | | | |
| Typical Properties | | Method | Value | Unit |
| Physical | | | | |
| Density (Method A) | | ISO 1183 | 0.90 | g/cm³ |
| Melt flow rate (MFR) (230°C/2.16Kg) | | ISO 1133 | 5.5 | g/10 min |
| Thermal | | | | |
| Melting temperature | | | 132 | °C |
| Note: ISO 11357-3 | | | | |
| Heat deflection temperature B (0.45 Unannealed | MPa) | ISO 75B-1, -2 | 62 | °C |
| Vicat softening temperature A/50 | | ISO 306 | 107 | °C |
| Optical | | | | |
| Haze (50 µm) | | ASTM D 1003 | 1 | % |
| Gloss (45°, 50 μm) | | ASTM D 2457 | 87 | |
| Film | | | | |
| Seal initiation temperature | | | 105 | °C |
| Note: Internal test method | | | | |
| | | | | |



