

Adflex Z 101 H

Advanced Polyolefin

Product Description

Adflex Z 101 H is a reactor TPO (thermoplastic polyolefin) manufactured using the LyondellBasell's proprietary *Catalloy* process technology.

It exhibits high softness and low modulus, with high melt flow index.

Adflex Z 101 H is tailored to replace atactic polypropylene copolymers (APP) used for the modification of bitumen in roofing membranes. The percentage to be added can vary according to the quantity of the atactic polypropylene used in combination with Adflex Z 101 H and the requested cold bending temperature of the end product. Its structure is tailored to obtain easy dispersion and phase inversion in the bitumen blend.

The grade is available in natural pellet form.

For regulatory compliance information see Adflex Z 101 H Regulatory Affairs Product Stewardship Information/Certification Data Sheet (RAPIDS), which can be found on www.polymers.lyondellbasell.com.

Product Characteristics

| | |
|--------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------|
| Status | Commercial: Active |
| Test Method used | ISO |
| Processing Methods | Extrusion Compounding, Injection Molding |
| Features | Good Chemical Resistance, High ESCR (Environmental Stress Cracking Resistance), Good Flexibility, High Flow , Low Temperature Impact Resistance, Soft |
| Typical Customer Applications | Bitumen Modification |

| Typical Properties | Method | Value | Unit |
|------------------------------------------------|---------------|----------|-------------------|
| Physical | | | |
| Density (Method A) | ISO 1183 | 0.88 | g/cm ³ |
| Melt flow rate (MFR) (230°C/2.16kg) | ISO 1133 | 27 | g/10 min |
| Mechanical | | | |
| Tensile Stress at Yield | ISO 527-1, -2 | 5 | MPa |
| Tensile Strain at Break | ISO 527-1, -2 | > 400 | % |
| Flexural modulus | ISO 178 | 76 | MPa |
| Impact | | | |
| Notched izod impact strength | ISO 180 | | |
| (- 20 °C, Type 1, Notch A) | | No Break | |
| (- 40°C, Type 1, Notch A) | | > 40 | kJ/m ² |
| Hardness | | | |
| Shore hardness (Shore D) | ISO 868 | 28 | |
| Thermal | | | |
| Vicat softening temperature (A50 (50°C/h 10N)) | ISO 306 | 55 | °C |

Notes

Typical properties; not to be construed as specifications.

