



Hifax 5519/1 G 1750

Compounded Polyolefin

Product Description

Hifax 5519/1 G 1750 is a less than 10% talc filled PP copolymer, with good impact resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 1750 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Impact resistance.
Typical Customer Applications	Used for automotive bumper.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	13	g/10 min
Density (23 °C)	ISO 1183-1/A	0.97	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	17	MPa
Tens.Strain at Break	ISO 527-1, -2	100	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1250	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	60	kJ/m ²
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	6.2	kJ/m ²
Thermal			
Vicat Softening Temperature A (10 N)	ISO 306	125	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	47	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.

