

## Dexflex 940D FP

### Compounded Polyolefin

#### Product Description

Dexflex 940D FP is a thermoplastic olefinic elastomer (TPO) designed for large automotive exterior, painted applications.

#### Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Processing Methods	Injection Molding
Features	Paintable
Typical Customer Applications	Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density	ISO 1183	0.98	g/cm <sup>3</sup>
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	22	g/10 min
<b>Mechanical</b>			
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	21	MPa
Flexural modulus (2 mm/min)	ISO 178	1300	MPa
Note: 80x10x4mm specimen			
<b>Impact</b>			
Multiaxial Impact Strength (23 °C, 2.2 m/s)	ASTM D3763	19	J
<b>Additional Information</b>			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrinkage recommendations.			

#### Notes

Typical properties; not to be construed as specifications.

