

Dexflex 1066LS-UV

Compounded Polyolefin

Product Description

 ${\it Dexflex}~1066 LS-UV~is~a~thermoplastic~olefinic~elastomer~(TPO)~designed~for~automotive~exterior~applications~that~require~excellent~low-temperature~toughness~in~large~injection~molded~parts.$

Product Characteristics

Status Commercial: Restricted

Test Method used ISO

Processing Methods Injection Molding

Features Low Temperature Toughness

Typical Customer Applications Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.91	g/cm³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	8	g/10 min
Mechanical			
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	15	MPa
Note: 150x10x4 mm specimen			
Flexural modulus (2 mm/min)	ISO 178	640	MPa
Note: 80x10x4mm specimen			
Additional Information			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrir	nkage recommendations		

Notes

Typical properties; not to be construed as specifications.



