

# Hifax TKC 238X BLACK

## **Compounded Polyolefin**

### **Product Description**

Hifax TKC 238X BLACK is a 20% talc filled PP copolymer, with low shrinkage and high flowability. Product is available in black color, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

**Status** Commercial

Processing Method Injection molding

**Features** Impact resistence, shrinkage.

**Typical Customer Applications** Used for automotive painted bumper fascias.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	12	g/10 min
Density (23 °C)	ISO 1183-1/A	1.05	g/cm <sup>3</sup>
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	12	MPa
Tens.Strain at Break	ISO 527-1, -2	80	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1500	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	60	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	4.7	kJ/m <sup>2</sup>
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	N.B.	kJ/m <sup>2</sup>
Thermal			
Vicat Softening Temperature A (10 N)	ISO 306	122	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	50	°C

## **Product Storage and Handling**

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- · Keep material completely dry for good processing.



