



Hifax TKC 220P C13098

Compounded Polyolefin

IMDS Number: 26755141

Product Description

Hifax TKC 220P C13098 is a 15% talc filled PP copolymer, with excellent scratch resistance and high impact resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C13098 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Scratch resistance, impact resistance.
Typical Customer Applications	Used for automotive exterior trims.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	14	g/10 min
Density (23 °C)	ISO 1183-1/A	0.99	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	19	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1400	MPa
Impact			
Izod Impact Strength, notched (-30 °C)	ISO 180/1A	5	kJ/m ²
Izod Impact strength, notched (23 °C)	ISO 180/1A	NB	kJ/m ²
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	95	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

