lyondellbasell

Hifax TRC 134P C11306

Compounded Polyolefin

Product Description

Hifax TRC 134P C11306 is a 20% talc filled PP copolymer, with very low shrinkage, good impact resistance and high UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C11306 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

| Status | Commercial |
|---|---|
| Processing Method | Injection molding |
| Features Typical Customer Applications | Shrinkage, impact resistance, UV resistance. Used for automotive partially painted bumper. |

| Typical Properties | Method | Value | Unit |
|--|---------------|-------|-------------------|
| Physical | | | |
| Melt Flow Rate (230 °C, 2.16 kg) | ISO 1133 | 20 | g/10 min |
| Density (23 °C) | ISO 1183-1/A | 1.05 | g/cm ³ |
| Mechanical | | | |
| Tens.Strain at Break | ISO 527-1, -2 | 500 | % |
| Flexural Modulus (23 °C) Tech. A | ISO 178/A1 | 1400 | MPa |
| Impact | | | |
| Charpy Impact Strength, notched (23 °C) | ISO 179-1/1eA | 61 | kJ/m ² |
| Charpy Impact Strength, notched (-30 °C) | ISO 179-1/1eA | 7 | kJ/m ² |

Product Storage and Handling

• Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

• Improper storage may bring damage to the packaging and can negatively affects on the quality of this product

• Keep material completely dry for good processing.



