# lyondellbasell Hifax TRC 447X BLACK

## Compounded Polyolefin

### **Product Description**

*Hifax* TRC 447X BLACK is a 22% talc filled PP copolymer, with high flowability and high stiffness. Product is available in black color, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

Status	Commercial
Processing Method	Injection molding
Features Typical Customer Applications	Flowability, stiffness. Used for automotive painted bumper and for heavy-truck applications.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	21	g/10 min
Density (23 °C)	ISO 1183-1/A	1.05	g/cm <sup>3</sup>
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	19	MPa
Tens.Strain at Break	ISO 527-1, -2	20	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	2300	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	15	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	4	kJ/m <sup>2</sup>

#### **Product Storage and Handling**

• Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

• Improper storage may bring damage to the packaging and can negatively affects on the quality of this product

• Keep material completely dry for good processing.



