lyondellbasell

. . ..

Hifax TRC 221P C11462

Compounded Polyolefin

Product Description

. ...

Hifax TRC 221P C11462 is a 20% talc filled PP copolymer, with high flowability, excellent impact/stiffness balance and very low CLTE. Product is available as a customized color matched, pellet form. This grade is delivered in C11462 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics	
Status	Commercial
Processing Method	Injection molding
Features	Impact/stiffness balance, CLTE (Coefficient of Linear Thermal Expansion).
Typical Customer Applications	Used for applications demanding high impact strength as well as good stiffness.

ypical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	15	g/10 min
Density (23 °C)	ISO 1183-1/A	1.04	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	16.5	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1500	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	55	kJ/m ²
Charpy Impact Strength, notched (-40 °C)	ISO 179-1/1eA	3.5	kJ/m ²
Izod Impact strength, notched (23 °C)	ISO 180/1A	48	kJ/m ²
Izod Impact strength, notched (-40 °C)	ISO 180/1A	5	kJ/m ²
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	95	°C

Product Storage and Handling

• Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

• Improper storage may bring damage to the packaging and can negatively affects on the quality of this product

• Keep material completely dry for good processing.



