

# Hifax TRS 260P C11319

## **Compounded Polyolefin**

### **Product Description**

Hifax TRS 260P C11319 is an unfilled PP copolymer, with very good processability and medium impact/stiffness balance. Product is available as a customized color matched, pellet form. This grade is delivered in C11319 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

**Status** Commercial

Processing Method Injection molding

**Features** Processability, impact/stiffness balance.

Typical Customer Applications Used for automotive interior trims.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	21	g/10 min
Density (23 °C)	ISO 1183-1/A	0.9	g/cm <sup>3</sup>
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	16.5	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	600	MPa
Impact			
Izod Impact strength, notched (23 °C)	ISO 180/1A	50	kJ/m <sup>2</sup>
Izod Impact strength, notched (-40 °C)	ISO 180/1A	8	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	55	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (-40 °C)	ISO 179-1/1eA	7	kJ/m <sup>2</sup>
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	64	°C

### **Product Storage and Handling**

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.



