

Hifax TRC 779XHS

Compounded Polyolefin

Product Description

Hifax TRC 779XHS high melt flow, medium high flexural modulus, paintable, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of properties and processability. It was designed for use in multiple automotive exterior applications.

Product Characteristics				
Status	Commercial: Active			
Test Method used	ISO			
Processing Methods	Injection Molding			
Typical Customer Applications	Exterior Applications			
Typical Properties	Method	Value	Unit	
Physical				

Physical				
Density (Method A)	ISO 1183	0.98	g/cm ³	
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	25	g/10 min	
Mechanical				
Flexural modulus (23 °C)	ISO 178	1500	MPa	
Tensile stress at yield	ISO 527	17	MPa	
Additional Information				
Mold shrinkage	ISO 294-4			
Note: Please contact LyondellBasell for shrinka	age recommendations			

Notes

Typical properties; not to be construed as specifications.



