



Hifax TRS 372P

Compounded Polyolefin

IMDS Number: 19523740

Product Description

Hifax TRS 372P is an unfilled PP copolymer, with excellent processability, excellent impact resistance and good UV resistance. The product is available in different color matched, pellet form. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Processability, impact resistance, UV resistance, surface appearance.
Typical Customer Applications	Used for applications that require excellent aesthetics and for automotive exterior trims.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	23	g/10 min
Density (23 °C)	ISO 1183-1/A	0.9	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	13	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	550	MPa
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	60	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

