# lyondellbasell

## Hifax TYC 2005P S62840

### **Compounded Polyolefin**

#### **Product Description**

*Hifax* TYC 2005P S62840 is a 14% talc filled PP copolymer, with very high flowability, high impact resistance and medium rigidity. This material has been coloured to create a metallic effect.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics	
Status	Commercial
Processing Method	Injection molding
Features Typical Customer Applications	Flowability, impact resistance, rigidity. Used for automotive exterior trims.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	26	g/10 min
Density (23 °C)	ISO 1183-1/A	1.02	g/cm <sup>3</sup>
Mechanical			
Tensile Strength (23 °C)	ISO 527-1, -2	16	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1350	MPa
Impact			
Izod Impact strength, notched (23 °C)	ISO 180/1A	45	kJ/m²
Izod Impact Strength, notched (-30 °C)	ISO 180/1A	5	kJ/m <sup>2</sup>
Thermal			
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	49	С°С
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	82	°C

#### **Product Storage and Handling**

• Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

• Improper storage may bring damage to the packaging and can negatively affects on the quality of this product

• Keep material completely dry for good processing.



