



## Hifax TYC 337P 2 S61467

### Compounded Polyolefin

#### Product Description

Hifax TYC 337P 2 S61467 is a 15% talc filled PP copolymer, with very high melt flow rate and good impact resistance. Product is available as a customized color matched, pellet form. This grade is delivered in S61467 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

#### Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Very high melt flow rate, impact resistance.
Typical Customer Applications	Used for any outdoor/exterior application.

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	25	g/10 min
Density (23 °C)	ISO 1183-1/A	1.02	g/cm <sup>3</sup>
<b>Mechanical</b>			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	16	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1350	MPa
<b>Thermal</b>			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	82	°C

#### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

