

# Hifax TYC 258P G14008

## **Compounded Polyolefin**

### **Product Description**

Hifax TYC 258P G14008 is a 30% talc filled PP copolymer, inpact modified and UV stabilized with excellent flowability, low coefficient of liner thermal expansion and good processability. Product is available as a customized color matched, pelletform. This grade is delivered in G14008 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

**Status** Commercial

Processing Method Injection molding

**Features** Flowability, UV resistance, dimensional stability.

**Typical Customer Applications** Used for automotive exterior trims.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	20	g/10 min
Density (23 °C)	ISO 1183-1/A	1.13	g/cm <sup>3</sup>
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	18	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1900	MPa
Flexural Strength (23 °C) Tech. A	ISO 178/A1	24	MPa
Impact			
Izod Impact strength, notched (23 °C)	ISO 180/1A	30	kJ/m <sup>2</sup>
Izod Impact Strength, notched (-30 °C)	ISO 180/1A	3.5	kJ/m <sup>2</sup>
Thermal			
Vicat Softening Temperature B (50 N)	ISO 306	50	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	54	°C

### **Product Storage and Handling**

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.



