

## Hostacom CR 1152 F C13034

### Compounded Polyolefin

#### Product Description

Hostacom CR 1152 F C13034 is a 10% mineral filled PP copolymer, with high impact resistance, very good impact/stiffness balance and high melt flow rate. Product is available as a customized color matched, pellet form. It has been designed using the latest advancements in resin synthesis and compounding technology. This grade is delivered in C13034 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

#### Product Characteristics

<b>Status</b>	Commercial
<b>Processing Method</b>	Injection molding
<b>Features</b>	Impact resistance, impact/stiffness balance, high melt flow rate
<b>Typical Customer Applications</b>	Used for automotive instrument panel design; the low density concept contributes to reduction of final aprt weight.

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	10	g/10 min
Density (23 °C)	ISO 1183-1/A	0.97	g/cm <sup>3</sup>
<b>Mechanical</b>			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1800	MPa
<b>Impact</b>			
Izod Impact Strength, notched (0 °C)	ISO 180/1A	7.5	kJ/m <sup>2</sup>
Izod Impact strength, notched (23 °C)	ISO 180/1A	25	kJ/m <sup>2</sup>
<b>Thermal</b>			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	106	°C

#### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

