



Hostacom BFR

Compounded Polyolefin

Product Description

Hostacom BFR is talc filled PP copolymer, with medium impact/stiffness balance and good flowability.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Impact/stiffness balance.
Typical Customer Applications	Used for standard applications.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	7	g/10 min
Density (23 °C)	ISO 1183-1/A	0.95	g/cm ³
Mechanical			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	900	MPa
Impact			
Izod Impact strength, notched (23 °C)	ISO 180/1A	15	kJ/m ²

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

