# lyondellbasell

## Hostacom BB 73 F 1648

### **Compounded Polyolefin**

#### **Product Description**

*Hostacom* BB 73 F 1648 is a 22% talc filled PP copolymer, with excellent flowability, high rigidity, high dimensional stability and good scratch resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 1648 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

Status	Commercial
Processing Method	Injection molding
Features Typical Customer Applications	Flowability, rigidity, dimensional stability. Used for moulding automotive interior large complex parts.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	21	g/10 min
Density (23 °C)	ISO 1183-1/A	1.06	g/cm <sup>3</sup>
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	21	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	2000	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	5	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (-40 °C)	ISO 179-1/1eA	2	kJ/m <sup>2</sup>
Izod Impact strength, notched (23 °C)	ISO 180/1A	5	kJ/m <sup>2</sup>
Izod Impact strength, notched (-40 °C)	ISO 180/1A	2.5	kJ/m <sup>2</sup>
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	100	°C

#### **Product Storage and Handling**

• Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

• Improper storage may bring damage to the packaging and can negatively affects on the quality of this product

• Keep material completely dry for good processing.



