

# Hostacom EKC 330N E1 D7V721

## **Compounded Polyolefin**

### **Product Description**

Hostacom EKC 330N E1 D7V721 is a 16% talc filled PP copolymer, with good flowability, excellent impact/stiffness balance, good scratch resistance and outstanding blooming resistance at elevated temperatures. The product is also available as a customized color matched, pellet form. This grade is delivered in D7V721 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

#### **Product Characteristics**

**Status** Commercial

Processing Method Injection molding

**Features** Impact/stiffness balance, scratch resistance.

Typical Customer Applications Used for automotive interior trims.

| Typical Properties                        | Method        | Value | Unit              |
|---|---------------|-------|-------------------|
| Physical                                  |               |       |                   |
| Melt Flow Rate (230 °C, 2.16 kg)          | ISO 1133      | 18    | g/10 min          |
| Density (23 °C)                           | ISO 1183-1/A  | 1.02  | g/cm <sup>3</sup> |
| Mechanical                                |               |       |                   |
| Tensile Stress at Yield (23 °C)           | ISO 527-1, -2 | 21    | MPa               |
| Flexural Modulus (23 °C) Tech. A          | ISO 178/A1    | 1800  | MPa               |
| Impact                                    |               |       |                   |
| Charpy Impact Strength, unnotched (23 °C) | ISO 179-1/1eU | NB    | kJ/m <sup>2</sup> |
| Charpy Impact Strength, notched (23 °C)   | ISO 179-1/1eA | 45    | kJ/m²             |
| Charpy Impact Strength, notched (-30 °C)  | ISO 179-1/1eA | 5     | kJ/m <sup>2</sup> |
| Thermal                                   |               |       |                   |
| Vicat Softening Temperature A (10 N)      | ISO 306       | 132   | °C                |
| Heat Deflection Temperature A (1.8 MPa)   | ISO 75-1, -2  | 56    | °C                |

### **Product Storage and Handling**

- · Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- · Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- · Keep material completely dry for good processing.



