

## Hostacom ERC 204N NAT

### Compounded Polyolefin

#### Product Description

Hostacom ERC 204N NAT is a 10% talc filled PP copolymer, with high stiffness, low filler content, good scratch resistance and low odour. Advanced technologies allowed for a significant reduction of mineral filler which contributed to the reduction of final part weight. The product is available as natural, pellet form.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

#### Product Characteristics

<b>Status</b>	Commercial
<b>Processing Method</b>	Injection molding
<b>Features</b>	Stiffness, density, scratch resistance, low odour. Low density contributes to reduction of final part weight.
<b>Typical Customer Applications</b>	Used for applications that require excellent aesthetics and for automotive interior trims.

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	20	g/10 min
Density (23 °C)	ISO 1183-1/A	0.97	g/cm <sup>3</sup>
<b>Mechanical</b>			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1900	MPa
<b>Impact</b>			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	6	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (0 °C)	ISO 179-1/1eA	4	kJ/m <sup>2</sup>
<b>Thermal</b>			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	100	°C

#### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

