



Hostacom ERC 213N G12404

Compounded Polyolefin

IMDS Number:

19524189

Product Description

Hostacom ERC 213N G12404 is a 14 % talc filled PP copolymer, with good flowability and excellent impact/stiffness balance. The product is also available as a customized color matched, pellet form. This grade is delivered in G12404 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Impact/stiffness balance, scratch resistance.
Typical Customer Applications	Designed for automotive interior trims.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	18	g/10 min
Density (23 °C)	ISO 1183-1/A	1.0	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	19	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1650	MPa
Impact			
Izod Impact strength, notched (23 °C)	ISO 180/1A	40	kJ/m ²
Izod Impact strength, notched (-40 °C)	ISO 180/1A	3	kJ/m ²
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	95	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

