lyondellbasell

Hostacom EYC 319N C12699

Compounded Polyolefin

IMDS Number:

19524189

Product Description

Hostacom EYC 319N C12699 is a 14% talc filled PP copolymer, with high flowability and good impact/stiffness balance. The product is available in different color matched, pellet form. This grade is delivered in C12699 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Commercial	
Processing Method	Injection molding	
Features Typical Customer Applications	Flowability, impact/stiffness balance. Used for automotive interior trims.	
Transis of Decementing		

ypical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	29	g/10 min
Density (23 °C)	ISO 1183-1/A	0.99	g/cm ³
Mechanical			
Tensile Strength (23 °C)	ISO 527-1, -2	20	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1600	MPa
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	100	°C

Product Storage and Handling

• Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

• Improper storage may bring damage to the packaging and can negatively affects on the quality of this product

· Keep material completely dry for good processing.



