

Hostacom G2 N01 102297

Compounded Polyolefin

Product Description

Hostacom G2 N01 102297 is a 20% milled glass fiber reinforced PP homopolymer without chemical coupling, with low flowability. The product is available in black color, pellet form. This grade is delivered in 102297 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Stiffness.
Typical Customer Applications	Used for automotive under-the-hood.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 5 kg)	ISO 1133	8	g/10 min
Melt Volume Rate (230 °C, 5 kg)	ISO 1133	9	cm ³ /10 min
Density (23 °C)	ISO 1183-1/A	1.05	g/cm ³
Mechanical			
Tensile Modulus (23 °C)	ISO 527-1, -2	3300	MPa
Impact			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	45	kJ/m ²
Charpy Impact Strength, unnotched (0 °C)	ISO 179-1/1eU	25	kJ/m ²
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	4	kJ/m ²
Thermal			
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	80	°C
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	120	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

