



Hostacom G3 N01 L303613

Compounded Polyolefin

Product Description

"Hostacom G3 N01 L303613 is a glass fiber reinforced PP homopolymer, with low melt flow rate. Product is UL listed."

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Low melt flow rate.
Typical Customer Applications	Used for appliances.

Typical Properties	Method	Value	Unit
Physical			
Density (23 °C)	ISO 1183-1/A	1.14	g/cm ³
Melt Volume Rate (230 °C, 2.16 kg)	ISO 1133	1	cm ³ /10 min
Melt Volume Rate (230 °C, 5 kg)	ISO 1133	5	cm ³ /10 min
Mechanical			
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	5500	MPa
Tensile Modulus (23 °C)	ISO 527-1, -2	6500	MPa
Tens.Strain at Break	ISO 527-1, -2	3.0	%
Tensile Stress at Break (23 °C)	ISO 527-1, -2	85	MPa
Impact			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	40	kJ/m ²
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	9.0	kJ/m ²
Thermal			
Vicat Softening Temperature B (50 N)	ISO 306	130	°C
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	155	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	140	°C
Other			
Flame Class (3.0 mm)	UL 94	HB	-
Flame Class (1.5 mm)	UL 94	HB	-

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

