



Hostacom PP HH42L 356015

Compounded Polyolefin

Product Description

"Hostacom PP HH42L 356015 is an unfilled PP homopolymer, with low melt flow rate. Product is UL listed."

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial
Processing Method	Extrusion
Features	Low melt flow rate.
Typical Customer Applications	Used for appliances.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 5 kg)	ISO 1133	1.5	g/10 min
Melt Volume Rate (230 °C, 5 kg)	ISO 1133	2.0	cm ³ /10 min
Density (23 °C)	ISO 1183-1/A	0.91	g/cm ³
Mechanical			
Tensile Modulus (23 °C)	ISO 527-1, -2	1500	MPa
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	38	MPa
Tensile Strain at Yield (23 °C)	ISO 527-1, -2	10.0	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1500	MPa
Impact			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	NB	kJ/m ²
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	8.0	kJ/m ²
Thermal			
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	55	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

