

Hostacom M2 U08 100000

Compounded Polyolefin

Product Description

Hostacom M2 U08 100000 is a 20% talc filled PP homopolymer, with good flowability. Product is available as a customized color matched, pellet form. This grade is delivered in Black color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status Commercial

Processing Method Injection molding

Features Flowability.

Typical Customer Applications Used for injection moulding general purpose.

| Typical Properties | Method | Value | Unit |
|---|---------------|-------|-------------------------|
| Physical | | | |
| Melt Flow Rate (230 °C, 2.16 kg) | ISO 1133 | 12 | g/10 min |
| Melt Volume Rate (230 °C, 2.16 kg) | ISO 1133 | 13 | cm ³ /10 min |
| Density (23 °C) | ISO 1183-1/A | 1.05 | g/cm ³ |
| Mechanical | | | |
| Tensile Stress at Yield (23 °C) | ISO 527-1, -2 | 39 | MPa |
| Impact | | | |
| Charpy Impact Strength, unnotched (23 °C) | ISO 179-1/1eU | 38 | kJ/m ² |
| Charpy Impact Strength, notched (23 °C) | ISO 179-1/1eA | 3.5 | kJ/m ² |
| Thermal | | | |
| Heat Deflection Temperature A (1.8 MPa) | ISO 75-1, -2 | 66 | °C |
| Heat Deflection Temperature B (0.45 MPa) | ISO 75-1, -2 | 120 | °C |

Product Storage and Handling

- · Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.



