

# Hostacom SB572C

# **Compounded Polyolefin**

#### **Product Description**

*Hostacom* SB572C fractional melt flow, 1,100 MPa flexural modulus, precolored, extrusion grade polypropylene copolymer has balanced strength and processability.

| Product Characteristics       |  |
|-------------------------------|--|
| Status                        | Commercial: Active   |
| Test Method used              | ASTM   |
| Processing Methods            | Extrusion Pipe Sheet and Semi Finished Products                                  |
| Features                      | Copolymer, Low Flow , Good Melt Strength , Good<br>Processability, High Strength |
| Typical Customer Applications | Panels & Profiles, Soft Profile & Sheets   |

| Typical Properties                        | Method           | Value | Unit     |
|---|------------------|-------|----------|
| Physical                                  |                  |       |          |
| Density -Specific Gravity                 | ASTM D 792       | 0.91  | g/cm³    |
| Melt Flow Rate (230°C/2.16kg)             | ASTM D 1238      | 0.6   | g/10 min |
| Mechanical                                |                  |       |          |
| Flexural Modulus                          | ASTM D 790       | 1100  | MPa      |
| Tensile Strength @ Yield                  | ASTM D 638       | 23    | MPa      |
| Tensile Strength @ Break                  | ASTM D 638       | 34    | MPa      |
| Tensile Elongation @ Brk                  | ASTM D 638       | 650   | %        |
| Impact                                    |                  |       |          |
| Notched Izod Impact                       | ASTM D 256       |       |          |
| (23 °C)                                   |                  | 530   | J/m      |
| (-30 °C)                                  |                  | 130   | J/m      |
| Additional Information                    |                  |       |          |
| Mold shrink, Linear-Flow                  | ASTM D 955       |       |          |
| Note: Please contact Basell for shrinkage | recommendations. |       |          |

## **Additional Properties**

Note: Mold shrinkage values are determined on laboratory injection molded 100 mm x 150 mm x 3.2 mm plaques and, as such, are not necessarily representative of actual field data. Since, for example, wall thickness, gate type and location, flow length and paint oven temperature affect final part dimensions, it is recommended that you contact your Basell representative before any tools are cut.

## Notes

Typical properties; not to be construed as specifications.



