lyondellbasell

Hostacom PPT X9037HS

Compounded Polyolefin

Product Description

Hostacom PPT X9037HS is an unfilled PP copolymer, with medium melt flow, very good toughness, very good stiffness and good UV resistance. This grade is delivered in natural color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| Product Characteristics | |
|---|---|
| Status | Commercial |
| Processing Method | Injection molding |
| Features Typical Customer Applications | Toughness, stiffness, UV resistance. Used for automotive interior trims. |

| Typical Properties | Method | Value | Unit |
|---|---------------|-------|-------------------|
| Physical | | | |
| Melt Flow Rate (230 °C, 2.16 kg) | ISO 1133 | 7.5 | g/10 min |
| Density (23 °C) | ISO 1183-1/A | 0.91 | g/cm ³ |
| Mechanical | | | |
| Tensile Stress at Yield (23 °C) | ISO 527-1, -2 | 19 | MPa |
| Tens.Strain at Break | ISO 527-1, -2 | 70 | % |
| Flexural Modulus (23 °C) Tech. A | ISO 178/A1 | 1000 | MPa |
| Impact | | | |
| Charpy Impact Strength, unnotched (23 °C) | ISO 179-1/1eU | NB | kJ/m ² |
| Charpy Impact Strength, notched (23 °C) | ISO 179-1/1eA | 35 | kJ/m ² |
| Charpy Impact Strength, notched (-30 °C) | ISO 179-1/1eA | 8 | kJ/m ² |
| Thermal | | | |
| Heat Deflection Temperature A (1.8 MPa) | ISO 75-1, -2 | 52 | °C |

Product Storage and Handling

• Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

• Improper storage may bring damage to the packaging and can negatively affects on the quality of this product

• Keep material completely dry for good processing.



