

Hostacom PPU X9067HS G41478

Compounded Polyolefin

Product Description

Hostacom PPU X9067HS G41478 is an unfilled PP copolymer, with high flowability, superior stiffness and high toughness. Product is available as a customized color matched, pellet form. This grade is delivered in G41478 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Stiffness, toughness.
Typical Customer Applications	Suitable for indoor/interior applications.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	15	g/10 min
Density (23 °C)	ISO 1183-1/A	0.91	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	26	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1450	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	10	kJ/m ²
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	N.B.	kJ/m ²
Thermal			
Vicat Softening Temperature A (10 N)	ISO 306	147	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	58	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

