lyondellbasell

Hostacom PPU X9067HS C12351

Compounded Polyolefin

IMDS Number:

19523740

Product Description

Hostacom PPU X9067HS C12351 is an unfilled PP copolymer, with high flowability, good impact/stiffness balance and high UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C12351 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

| Status | Commercial |
|-------------------------------|---|
| Processing Method | Injection molding |
| Features | Flowability, impact/stiffness balance, UV resistance. |
| Typical Customer Applications | Designed for automotive interior trims. |

| Typical Properties | Method | Value | Unit |
|--|---------------|-------|-------------------|
| Physical | | | |
| Melt Flow Rate (230 °C, 2.16 kg) | ISO 1133 | 15 | g/10 min |
| Density (23 °C) | ISO 1183-1/A | 0.91 | g/cm ³ |
| Mechanical | | | |
| Tensile Stress at Yield (23 °C) | ISO 527-1, -2 | 26 | MPa |
| Tens.Strain at Break | ISO 527-1, -2 | 100 | % |
| Flexural Modulus (23 °C) Tech. A | ISO 178/A1 | 1450 | MPa |
| Impact | | | |
| Charpy Impact Strength, notched (23 °C) | ISO 179-1/1eA | 9 | kJ/m ² |
| Charpy Impact Strength, notched (-30 °C) | ISO 179-1/1eA | 4 | kJ/m ² |
| Thermal | | | |
| Vicat Softening Temperature A (10 N) | ISO 306 | 145 | °C |
| Heat Deflection Temperature B (0.45 MPa) | ISO 75-1, -2 | 100 | °C |

Product Storage and Handling

• Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

• Improper storage may bring damage to the packaging and can negatively affects on the quality of this product

· Keep material completely dry for good processing.



