



Hifax TKC 243P C1V301

Compounded Polyolefin

Product Description

Hifax TKC 243P C1V301 is a 10% talc filled PP copolymer, with good impact/stiffness balance and high UV resistance. The product is available as a customized color matched, pellet form. This grade is delivered in C1V301 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Impact/stiffness balance, UV resistance.
Typical Customer Applications	Used for automotive unpainted bumper.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	11	g/10 min
Density (23 °C)	ISO 1183-1/A	0.97	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	17	MPa
Tens.Strain at Break	ISO 527-1, -2	80	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1350	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	60	kJ/m ²
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	5	kJ/m ²
Thermal			
Vicat Softening Temperature A (10 N)	ISO 306	130	°C
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	90	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

