



## Hostacom TRC 333N D22713

Compounded Polyolefin

IMDS Number: 19524190

### Product Description

Hostacom TRC 333N D22713 is a 20% talc filled PP copolymer, with high flowability, high stiffness, high UV resistance, very good scratch resistance and low emissions. Product is available as a customized color matched, pellet form. This grade is delivered in D22713 color version.

*This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.*

### Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Flowability, stiffness, UV resistance, scratch resistance and low emissions.
Typical Customer Applications	Designed for automotive interior trims.

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	17	g/10 min
Density (23 °C)	ISO 1183-1/A	1.05	g/cm <sup>3</sup>
<b>Mechanical</b>			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	21	MPa
Tens.Strain at Break	ISO 527-1, -2	75	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	2000	MPa
<b>Impact</b>			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	15	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	3	kJ/m <sup>2</sup>
<b>Thermal</b>			
Vicat Softening Temperature A (10 N)	ISO 306	130	°C
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	95	°C

### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

