

# Hostacom TRC 333N D72643

# **Compounded Polyolefin**

### **Product Description**

Hostacom TRC 333N D72643 is a 20% talc filled PP copolymer, with high flowability, high stiffness, high UV resistance, very good scratch resistance and low emissions. Product is available as a customized color matched, pellet form. This grade is delivered in D72643 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

#### **Product Characteristics**

**Status** Commercial

Processing Method Injection molding

**Features** Flowability, stiffness, UV resistance, scratch resistance and low emissions.

Typical Customer Applications Used for automotive interior trims.

| Typical Properties                       | Method        | Value | Unit              |
|--|---------------|-------|-------------------|
| Physical                                 |               |       |                   |
| Melt Flow Rate (230 °C, 2.16 kg)         | ISO 1133      | 17    | g/10 min          |
| Density (23 °C)                          | ISO 1183-1/A  | 1.05  | g/cm <sup>3</sup> |
| Mechanical                               |               |       |                   |
| Tensile Stress at Yield (23 °C)          | ISO 527-1, -2 | 21    | MPa               |
| Tens.Strain at Break                     | ISO 527-1, -2 | 75    | %                 |
| Flexural Modulus (23 °C) Tech. A         | ISO 178/A1    | 2000  | MPa               |
| Impact                                   |               |       |                   |
| Charpy Impact Strength, notched (23 °C)  | ISO 179-1/1eA | 15    | kJ/m <sup>2</sup> |
| Charpy Impact Strength, notched (-30 °C) | ISO 179-1/1eA | 3     | kJ/m <sup>2</sup> |
| Thermal                                  |               |       |                   |
| Vicat Softening Temperature A (10 N)     | ISO 306       | 130   | °C                |
| Heat Deflection Temperature B (0.45 MPa) | ISO 75-1, -2  | 95    | °C                |

## **Product Storage and Handling**

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- · Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- · Keep material completely dry for good processing.



