

Hostacom X M3 T14 151237

Compounded Polyolefin

Product Description

Hostacom X M3 T14 151237 is a 28% talc filled PP copolymer, with medium melt flow, good UV resistance, low odour, low fogging and low emissions. Product is available as a customized color matched, pellet form. This grade is delivered in 151237 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	UV resistance, low odour, low emissions.
Typical Customer Applications	Used for automotive interior trims.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	7	g/10 min
Density (23 °C)	ISO 1183-1/A	1.14	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	24	MPa
Tens.Strain at Break	ISO 527-1, -2	5	%
Impact			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	40	kJ/m ²
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	8	kJ/m ²
Thermal			
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	65	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

