

Hostacom X M2 V05 M C12463

Compounded Polyolefin

Product Description

Hostacom X M2 V05 M C12463 is a 20% talc filled PP copolymer, with good flowability and high stiffness. Product is available as a customized color matched, pellet form. This grade is delivered in C12463 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial
Processing Method	Injection molding
Features	Flowability, stiffness.
Typical Customer Applications	Used for automotive interior trims.

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	20	g/10 min
Density (23 °C)	ISO 1183-1/A	1.05	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	22	MPa
Impact			
Charpy Impact Strength, notched (-40 °C)	ISO 179-1/1eA	1.5	kJ/m ²
Izod Impact strength, notched (-40 °C)	ISO 180/1A	2	kJ/m ²
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	5	kJ/m ²
Izod Impact strength, notched (23 °C)	ISO 180/1A	4.5	kJ/m ²
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	110	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

