

Toppyl SP 2000 B

Compounded Polyolefin

Product Description

 $\label{eq:constraint} \textbf{ToppyI SP 2000 B} is a fully formulated seal peel solution especially developed for the blown film technology.$

This product has been designed to offer a peelable seal to PE substrates or to seal & peel against itself and is suitable for non-sterilisable applications.

Toppyl SP 2000B is a solution created to replace completely the sealing layer in a coextruded film.

It provides a constant easy-opening force over a wide sealing temperature window and is readily processable on conventional equipment in both mono and co-extruded structures. EU and FDA compliance information about this product can be found in separate product documentation.

This product is not intended for use in medical and pharmaceutical applications.

Product Characteristics Status Commercial: Active **Test Method used** ISO $\begin{array}{l} \mbox{Medium Antiblocking , Semi Crystalline, Good Heat Seal,} \\ \mbox{Good Melt Strength , Medium Slip, Good Tear Strength} \end{array}$ Features **Typical Customer Applications** Blown Film, Peelable Film, Speciality Film **Typical Properties** Method Value Unit Physical Density ISO 1183 0.912 g/cm³ Melt flow rate (MFR) ISO 1133 2.0 g/10 min Mechanical Tensile Strength @ Brk MD ASTM D 882 28 MPa Tensile Strength @ Yld MD ASTM D 882 9 MPa ASTM D 882 670 Elongation at break MD % Thermal °C DSC 110 Melting temperature °C Vicat softening temperature A/50 ISO 306 90 Film 0.25 **Coefficient of Friction** ASTM D 1894 Secant modulus MD ASTM D 882 185 MPa

Additional Properties

Recommended processing temperatures: 170°C to 230°C. In cases were higher temperatures are required please contact your appropriate technical contact for support.

Notes

Typical properties; not to be construed as specifications.



