

# Softell DKG250N

## **Compounded Polyolefin**

#### **Product Description**

Softell DKG250N is a 25% glass filled, thermoplastic polyolefin elastomer compound for injection molding. The grade has been designed primarily for automotive interior applications that require low gloss, soft touch, very high rigidity, impact and good scratch and mar resistance.

### **Product Characteristics**

Status Commercial: Active

Test Method used ISO

Processing Methods Injection Molding

Features Ductile, Low Gloss, High Impact Resistance , Scratch

Resistant, Soft

Typical Customer Applications Interior Applications

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	15	g/10 min
Density (23°C)	ISO 1183	1.06	g/cm³
Mechanical			
Tensile Stress at Yield (23°C)	ISO 527-1, -2	42	MPa
Tensile Strain at Yield (23°C)	ISO 527-1, -2	12	%
Flexural modulus (23°C)	ISO 178	2750	MPa
Impact			
Notched izod impact strength	ISO 180		
(23°C)		42	kJ/m²
(-30°C)		20	kJ/m²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	142	°C
Additional Information			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrinkage reco	ommendations.		

#### **Notes**

Typical properties; not to be construed as specifications.



